

DIAMETERS

- 1.00in/25mm
- 1.50in/38mm
- 1.75in/44mm
- 2.00in/51mm
- 2.50in/64mm
- 3.00in/76mm

MTFS-800-DP®

Designed for normal day to day wear and tear

- » It's light weight reduces fire fighter fatigue and stress
- » Tough and ready for action
- » Unique Mertex® lining
- » Premium all synthetic double jacke
- » Available with the Identify® recessed area for color coding, bar coding and/or identification markings
- » Standard with Permatek HP™ treatment against abrasion, moisture pick up and mildew
- » Resistant to most chemicals, petrol products, ozone and U.V. exposure, and hydrolysis
- » Remains flexible to -65° F (-55° C).
- » Meets or exceeds all performance requirements of NFPA 1961, Underwriters Laboratories and Factory Mutual
- » Meets ULC requirements and can be labeled upon request in the sizes* specified below



Hose Spec.	Trade Size		Bowl Size		Weight Un-coiled 50' (15.2m)		Coil Diameter 50' (15.2m)		Service Pressure		Proof Pressure		Burst Pressure	
	In.	mm	In.	mm	Lbs	Kg	In.	Cm.	PSI	kPa	PSI	kPa	PSI	kPa
422	1.00	25	1 9/32	33	7.0	3.2	14.5	36.8	400	2 755	800	5 515	1 200	8 275
417	1.5*	38*	1 13/16	46	10.5	4.8	14.5	36.8	400	2 755	800	5 515	1 200	8 275
418	1.75*	44*	2	51	12.0	5.5	14.5	36.8	400	2 755	800	5 515	1 200	8 275
419	2*	51*	2 5/16	59	16.0	7.3	15.5	39.4	400	2 755	800	5 515	1 200	8 275
420	2.5*	64*	2 7/8	73	19.0	8.6	16.0	40.6	400	2 755	800	5 515	1 200	8 275
421	3*	76*	3 5/16	84	25.5	11.6	16.0	40.6	400	2 755	800	5 515	1 200	8 275



**MERCEDES
TEXTILES LIMITED**

5838 Cypihot
Saint Laurent, QC
Canada, H4S 1Y5

PHONE 514.335.4337
PHONE 877.937.9660
FAX 514.335.9633

mercedestextiles.com
sales@mercedestextiles.com

HOW TO SPECIFY

MTFS-800-DP®

THE HOSE SHALL BE DOUBLE JACKET WITH SERVICE TEST PRESSURES AS SPECIFIED ON THE PREVIOUS PAGE

.....

JACKETS

The inner alone shall be an NFPA compliant Attack hose, made with 100% filament polyester warp and weft yarn.

The outer jacket shall be made with virgin spun polyester warp yarn and a minimum of 10 filament polyester weft yarn picks per inch (394 per Meter). The outer jacket shall be impregnated in one of the standard NFPA colors with high performance polymeric dispersion.

LINING

The lining (waterway) must be made from polyurethane and must be applied using a fused process that welds the polyurethane directly to the textile while the hose is being woven, without the use of adhesives or hot melt. This process allows for the use of high strength Filament Polyester warp and weft yarn due to the superior liner adhesion, and locks fibers together for greater strength while still allowing for a high flexibility. The fused lining process must create a virtually inseparable unit without the use of adhesives, yielding an extremely low friction (pressure) loss by filling in the corrugations of the weave, creating an amazingly thin and smooth waterway. This process produces lower elongation under pressure, and less pull back when water pressure is suddenly shut-off, resulting in a safer hose to work with. The lining shall be approved for use with potable water.

ADHESION

The adhesion shall be such that the rate of separation of a 1 1/2" / 38mm strip of polyurethane, transversely cut, shall not be greater than 1/4" / 6mm per minute under a weight of 12 lbs / 5.5 kg.

COLD TEMPERATURE FLEXIBILITY

The hose must remain flexible to -65°F (-55°C).

FLOW AND FRICTION LOSS

1 3/4 inch (44mm) diameter, 100 US GPM (379 LPM), shall not exceed 8.5 PSI (59 KPa) loss per 100 feet (30.5 M).

SERVICE, TEST, BURST PRESSURES

Minimum service, test and burst pressures shall be as detailed in the specification table on the previous page.

KINK TEST

A full length will withstand a hydrostatic pressure of 600 psi / 4140 kPa while kinked.

WEIGHT

Each length of fire hose shall not weigh more than indicated in the specification table.

COUPLING SPECIFICATIONS

The Hard Coat anodized couplings shall be manufactured in North America, and permanently labeled with country of origin. They shall be expansion ring type. The male coupling and female swivel nut must both have a recessed area to facilitate color and bar coding and/or identification markings.

MANUFACTURE

Both hose and couplings must be manufactured in North America and be NAFTA compliant.

INNOVATION DELIVERED.